

Crystal paper bags

Property	Measurement Unit	Test Method	Standard	Range
Paper Substance	g/m ²	ISO 536	35	34 - 36
Thickness	µm	ISO 534	36	36
Tensile Strength MD	kN/m	ISO 1924-2	3.5	3.4 - 3.6
Tensile Strength CD	kN/m	ISO 1924-2	1.6	1.5 - 1.7
Burst Strength	kPa	DIN53113	180	175 - 185
Seam Strength	N	N	3.5	3.5 - 4.5
Flap Closure Strength	N	N	1.2	0.8 - 1.2
Transparency	%	DIN 53147	68	67 - 69